



# Den Braven

## Technical Data Sheet

### Zwaluw Silicone NO MFT

Neutrally curing silicone



#### Product Description

Zwaluw Silicone NO MFT is a versatile neutral silicone sealant for sanitary, building, glazing and façade joints, which cures under influence of humidity to form a durable elastic rubber.

#### Benefits

- Connecting joints in buildings
- Top sealing in glazing systems
- Sanitary applications

#### Applications

Zwaluw Silicone NO MFT was specifically developed for durable elastic sealing of expansion joints in many building materials to precast concrete and brickwork. Den Braven Silicone NO MFT can also be applied as parameter and curtain wall sealing, glazing systems and cap beading and for kitchens, bathrooms and showers.

#### Directions Of Use

A joint with the correct dimensions is able to absorb movements between building materials. The joint depth should always be in the correct relationship of the joint width. A general rule is the ratio of joint depth to the width of the joint with a joint width up to 10 mm is 1:1, with a minimum of 5 mm in width and depth. For joints wider than 10 mm, the depth is the width divided by 3 plus 6 mm. For more information see the Technical Bulletin Joint Dimensions in the Knowledge Base on our website [www.denbraven.com](http://www.denbraven.com).

#### Additional information

100 % modulus	DIN 53504 S2	0,35 N/mm <sup>2</sup>
Application temperature		+5°C to +40°C
Base		Neutral oxime
Curing time	@ +23°C/50% RH	mm/24 hours
Density	ISO 1183-1	1,00 g/ml
Frost resistance during transportation		Up to -15°C
Shorea hardness	DIN 53505	15
Skin formation	DBTM 16	8 minutes @ +23°C/50% RH
Temperature resistance		-40°C to +120°C
Tensile strength	DIN 53504 S2	1,25 N/mm <sup>2</sup>

*These are typical values*

#### Limitations

- Not suitable for aquariums and terrariums
- Discoloration can occur in dark places and by contact with chemicals

#### Surface Preparations and Finishing

##### Paintability

Zwaluw Silicone NO MFT is not paintable.

##### Cleaning

Uncured material and tools can be cleaned by using Den Braven Cleaner. Cured material can only be mechanically removed. Hands can be cleaned with Den Braven Wipes.

##### Colour(s)

- White

##### Packaging

- Cartridge



Den Braven

Better  
results  
through  
knowledge

## Technical Data Sheet

### Zwaluw Silicone NO MFT



Neutrally curing silicone

*For product specifications, please refer to the Product Detail Page*

#### Shelf Life

In unopened original packaging between +5°C and +25°C, shelf life is up to 12 months from production date, stored in a dry place.

#### Certifications

	A+ French VOC Regulation
	EN 15651-1: F-EXT-INT-CC 12.5E EN 15651-3: S XS2
	EN 15651-2: G-CC

#### Health & Safety

Product Safety Data Sheet must be read and understood before use. These are available on request and via the Den Braven websites.

#### Warranty & Guarantee

Den Braven warrants that its product complies, within its shelf life, to its specification.

#### Disclaimer

All information in this document and in all our other publications (including electronic ones) is based on our current knowledge and experience and is the exclusive (intellectual) property of Den Braven. No part of this document may be copied, shown to third parties, reproduced, communicated to the public or used in any other way without Den Braven's written consent. The technical information in this document serves as an indication and is non-exhaustive. Den Braven is not liable for any damage, either direct or indirect, due to (editorial) errors, incompleteness and/or incorrectness of this document. This includes, but is not limited to, incompleteness and/or incorrectness due to technological changes or any research conducted between the date of publication of this document and the date on which the product is acquired. Den Braven reserves the right to amend the wording of this document. Den Braven cannot be held liable for any damage, either direct or indirect, due to the use of the product depicted in this document. The user must read and understand the information in this document and other documents relating to the products prior to the use the product. The user is responsible for performing all the requisite tests to make sure that the product is suitable for its intended use. We have no influence in what way the product is applied and/or any circumstances relating to events occurring during storage or transport and therefore we do not accept any liability for damage. All deliveries are made exclusively in accordance with our general terms of conditions which have been filed at the Dutch Chamber of Commerce.