



Den Braven

Technical Data Sheet

Zwaluw Hottix

One-component sealant for secondary sealing of insulating glass



Product Description

Solvent-free product, used for the manufacturing of double or triple insulating glass units, both for manual and for automated application technologies. Remark: MSDS available on request

Benefits

- Excellent adherence
- Easy to apply
- Short curing time, of approximately 30 minutes

Applications

Recommended for application at temperatures ranging between +165°C and +185°C, by means of proper extruding machines. The temperature of the application surface be $\geq 15^{\circ}\text{C}$, for optimal adhesive performance.

Directions Of Use

The product is applied at a temperature of +165°C and +185°C, using appropriate extruder. Surface temperature application must be $\geq 15^{\circ}\text{C}$ to ensure optimal adhesion.

Additional information

Application temperature		Extrusion between +165°C and +185°C surface temperature application will be $\geq 15^{\circ}\text{C}$
Base		Butyl rubber
Curing time		30 minutes
Density		1,10 [gr/cm ³]
Elongation at break	EN 1279/4	Approximately 120N/25 mm
Joint movement	EN 1279/4	Approximately 20 [%]

These are typical values

Limitations

- Before use test compatibility of all materials that may come in contact with the product

Surface Preparations and Finishing

The compatibility of all the materials which might come into contact with the product must be checked before use.

Cleaning

Colour(s)

- Black

Packaging

- Box

For product specifications, please refer to the Product Detail Page

Shelf Life

Health & Safety

Product Safety Data Sheet must be read and understood before use. These are available on request and via the Den Braven websites.



Den Braven

Technical Data Sheet

Better
results
through
knowledge

Zwaluw Hottix

One-component sealant for secondary sealing of insulating glass

Warranty & Guarantee

Den Braven warrants that its product complies, within its shelf life, to its specification.

Disclaimer

All information in this document and in all our other publications (including electronic ones) is based on our current knowledge and experience and is the exclusive (intellectual) property of Den Braven. No part of this document may be copied, shown to third parties, reproduced, communicated to the public or used in any other way without Den Braven's written consent. The technical information in this document serves as an indication and is non-exhaustive. Den Braven is not liable for any damage, either directly or indirectly, due to (editorial) errors, incompleteness and/or incorrectness of this document. This includes, but is not limited to, incompleteness and/or incorrectness due to technological changes or any research conducted between the date of publication of this document and the date on which the product is acquired. Den Braven reserves the right to amend the wording of this document. Den Braven cannot be held liable for any damage, either directly or indirectly, due to the use of the product(s) depicted in this document. The user must read and understand the information in this document and other documents relating to the products prior to the use of the product. The user is responsible for performing all the requisite tests to make sure that the product is suitable for its intended use. We have no influence in what way the product is applied and/or any circumstances relating to events occurring during storage or transport and therefore we do not accept any liability for damage whatsoever. All deliveries are made exclusively in accordance with our general terms of conditions which have been filed at the Dutch Chamber of Commerce.



Den Braven

Den Braven Sealants S.A. (Pty) Ltd.
2 Highview Boulevard, Ferndale Extension 26, Randburg, Gauteng
T +27 117923830 | E sales@denbraven.co.za

17-05-2024
08:48:03
CEST