



# Den Braven

## Technical Data Sheet

### Hercuseal Superior Outdoor 130

High quality fast rain resistant acrylic sealant for interior and exterior use



#### Product Description

Hercuseal Superior Outdoor 130 is a high quality acrylic sealant which is rain resistant soon after application. After application the product cures to a plasto-elastic rubber due to evaporation of water from the sealant.

#### Benefits

- Rain resistant soon after application
- Interior and exterior uses
- High elongation at break and high movement accomodation
- Paintable with water based and synthetic paints
- Perfect adhesion without use of a primer on most, even slightly damp substrates
- Almost odourless
- Easy to apply and clean
- Non corrosive towards metals
- Excellent tooling properties

#### Applications

Hercuseal Superior Outdoor 130 was specifically developed for connection joints between windowsills, stairs, ceilings, walls, skirtings, aerated concrete, plasterboard, limestone, wooden and metal window frames, concrete and brickwork. For interior and exterior use. As the sealant is rain resistant so soon after application, there are more possible applications.

#### Directions Of Use

A joint with the correct dimensions is able to absorb movements between building materials. The joint depth should always be in the correct relationship of the joint width. A general rule is the ratio of joint depth to the width of the joint with a joint width up to 10 mm is 1:1, with a minimum of 5 mm in width and depth. For joints wider than 10 mm, the depth is the width divided by 3 plus 6 mm. For more information see the Technical Bulletin Joint Dimensions in the Knowledge Base on our website [www.denbraven.com](http://www.denbraven.com).

#### Additional information

100 % modulus	DIN 53504 S2	0,10 N/mm <sup>2</sup>
Application rate	@ Ø3 mm/4 bar	500 g/min
Application temperature		+5°C to +40°C
Base		Acrylic dispersion
Curing time	@ +23°C/50% RH	2 mm/24 hours
Density		1,57 g/ml
Elongation at break	DIN 53505/ ISO 868	500%
Flow	ISO 7390	< 2 mm
Frost resistance during transportation		Up to -15°C
Joint movement		12,5%
Shorea hardness	DIN 53505	10
Skin formation	DBTM 16	10 minutes @ +23°C/50% RH
Temperature resistance		-20°C to +75°C
Tensile strength	DIN 53504	0,10 N/mm <sup>2</sup>

*These are typical values*

#### Limitations

- Not suitable for PE, PP, PC, PMMA, PTFE, soft plastics, neoprene and bituminous substrates
- Although the product is rain resistant, it will not withstand heavy driving rain and hail during curing



Den Braven

Bostik Singapore  
1 Science Park Road, #04-01/5 The Capricorn, 117528 Singapore  
T +65 6419 9161 | E

18-05-2024  
10:22:29  
CEST



Den Braven

## Technical Data Sheet

### Hercuseal Superior Outdoor 130

High quality fast rain resistant acrylic sealant for interior and exterior use

#### Surface Preparations and Finishing

Application temperature +5°C to +40°C (applies to environment and substrates). All substrates must be solid, clean, dry, and free of grease and dust. Substrates to be cleared of all loose particles, absorbent substrates do not need to be absolutely dry. Very porous substrates like: gypsum, airated concrete, limestone, etc, need to be primed with a mixture of 1 part Hercuseal Superior Outdoor 130 and 2 parts water. Always test adhesion prior to application. Finish and smooth with water.

#### Paintability

Hercuseal Superior Outdoor 130 is paintable when fully dry. During curing product will show shrinkage, which can cause cracking of the paint. Paintable with water based and synthetic paints. Painting with high water based paints can create cracking. We recommend testing compatability with paint prior to application.

#### Cleaning

Tools to be cleaned after use with water. Hands can be cleaned with Zwaluw Wipes and/or water and soap.

#### Colour(s)

- Grey
- Brown
- White

#### Packaging


- Cartridge



*For product specifications, please refer to the Product Detail Page*

#### Shelf Life

In unopened original packaging between +5°C and +25°C, shelf life till 18 months after production date, stored in a dry place.

#### Certifications

	EN 15651-1: F-EXT-INT 12.5P
-------------------------------------------------------------------------------------	-----------------------------

	Emicode EC1 Plus
	A+ French VOC Regulation

#### Health & Safety

Product Safety Data Sheet must be read and understood before use. These are available on request and via our websites

#### Warranty & Guarantee

Bostik warrants that its product complies, within its shelf life, to its specification.

#### Disclaimer

All information in this document and in all our other publications (including electronic ones) is based on our current knowledge and experience and is the exclusive (intellectual) property of Bostik. No part of this document may be copied, shown to third parties, reproduced, communicated to the public or used in any other way without Bostik written consent. The technical information in this document serves as an indication and is non-exhaustive. Bostik is not liable for any damage, either directly or indirectly, due to (editorial) errors, incompleteness and/or incorrectness of this document. This includes, but is not limited to, incompleteness and/or incorrectness due to technological changes or any research conducted between the date of publication of this document and the date on which the product is acquired. Bostik reserves the right to amend the wording of this document. Bostik cannot be held liable for any damage, either directly or indirectly, due to the use of the product(s) depicted in this document. The user must read and understand the information in this document and other documents relating to the products prior to the use of the product. The user is responsible for performing all the requisite tests to make sure that the product is suitable for its intended use. We have no influence in what way the product is applied and/or any circumstances relating to events occurring during storage or transport and therefore we do not accept any liability for damage whatsoever. All deliveries are made exclusively in accordance with our general terms of conditions which have been filed at the Dutch Chamber of Commerce.