



Den Braven

Technical Data Sheet

SX Mighty Strength Grip & Grab Adhesive

Ultra strength instant grab adhesive



Product Description

An incredible, instant grab adhesive based on MS Polymer technology. It has initial bond strength double that of most other grab adhesives and bonds to vertical surfaces without slippage, eliminating the need for secondary support in the majority of applications. Can even be used on damp or wet surfaces, is solvent free and cures quickly. It is water, frost and heat resistant from temperatures of -40°C to $+90^{\circ}\text{C}$ meaning it can be used externally as well as internally. An excellent alternative fixing adhesive which remains flexible, that replaces nails, screws and other mechanical fixings.

Benefits

- High initial grab - to bond heavy building materials without the use of clamps and/or fixing tape
- High strength, high E-modulus and high mechanical resistance, anti-pick and burglar proof
- Durable elasticity and fast curing
- No shrinkage and bubble free
- Non corrosive to metals
- Neutral curing, almost odourless
- Good resistance to weather and water
- Adheres perfectly without primer on most, even damp surfaces
- Free of isocyanates, phthalates, solvents and silicones
- Absorbs acoustic and mechanical vibrations

Applications

Suitable for bonding most building substrates but in particular, for fixing of large panels, wallboards and mirrors. Ideal for bonding brick slips, claddings and sanitary fixtures. Can also be used to fix dado rails, windowsills and decorative mouldings; it will adhere to virtually everything including wood, natural stone, mirrors, concrete, metal, mortar, bricks, gypsum and glass.

Directions Of Use

Cut the cartridge seal and screw on the pre-cut 'V' notched nozzle which must be used to ensure correct depth of adhesive is extruded. We recommend that a good quality skeleton gun is used due to that, by its nature, the product is stiff to gun. Apply the adhesive on one surface only in vertical strips, approximately 10-20 cm apart. Immediately place item into position with good, even pressure to give an excellent initial grab. On extremely heavy items, temporary support may be necessary during the curing process. Mechanical fixings should always be used in overhead applications.

Better
results
through
knowledge



Den Braven

Bostik Singapore
1 Science Park Road, #04-01/5 The Capricorn, 117528 Singapore
T +65 6419 9161 | E

28-04-2024
16:00:54
MDT



Den Braven

Technical Data Sheet

SX Mighty Strength Grip & Grab Adhesive

Ultra strength instant grab adhesive

Additional information

100 % modulus	DIN 53504 S2	1,39 N/mm ²
Application rate	@ Ø2,5 mm/6,3 bar	10-20 g/min
Application temperature		+5°C to +40°C
Base		Hybrid
Curing time	@ +23°C/50% RH	2-3 mm/24 hours
Density	ISO 1183-1	1,55 g/ml
Elongation at break	DIN 53504 S2	350%
Flow	ISO 7390	< 2 mm
Frost resistance during transportation		Up to -15°C
Shorea hardness	DIN 53505 3 sec.	55
Skin formation	DBTM 16	10 minutes @ +23°C/50% RH
Temperature resistance		-40°C to +90°C
Tensile strength	DIN 53504 S2	2,20 N/mm ²

These are typical values

Limitations

- Not suitable for PE, PP, PC, PMMA, PTFE, soft plastics, neoprene and bituminous substrates
- Not suitable for continuous exposure to water
- Not suitable for movement joints
- Not suitable in combination with chlorides (pools)

Surface Preparations and Finishing

Surfaces must be clean, dry and free from dust, grease and other loose material. Adhesion tests prior to application are recommended.

Cleaning

Cured material can only be mechanically removed. Hands can be cleaned with SX Multi-Purpose Cleaning Wipes.

Issue 7/29.04.16/0266.3.HS

Colour(s)

- White

Packaging





- Cartridge

For product specifications, please refer to the Product Detail Page

Shelf Life

Store between +5°C and +25°C and in shaded conditions. Shelf life is 18 months when stored as recommended in original unopened packaging.

Certifications

	Emicode EC1 Plus
	M1
	A+ French VOC Regulation
	ISEGA

Health & Safety

Product Safety Data Sheet must be read and understood before use. These are available on request and via our websites



Den Braven

Bostik Singapore
1 Science Park Road, #04-01/5 The Capricorn, 117528 Singapore
T +65 6419 9161 | E

28-04-2024
16:00:54
MDT



Den Braven

Technical Data Sheet

SX Mighty Strength Grip & Grab Adhesive

Ultra strength instant grab adhesive

Warranty & Guarantee

Bostik warrants that its product complies, within its shelf life, to its specification.

Disclaimer

All information in this document and in all our other publications (including electronic ones) is based on our current knowledge and experience and is the exclusive (intellectual) property of Bostik. No part of this document may be copied, shown to third parties, reproduced, communicated to the public or used in any other way without Bostik written consent. The technical information in this document serves as an indication and is non-exhaustive. Bostik is not liable for any damage, either directly or indirectly, due to (editorial) errors, incompleteness and/or incorrectness of this document. This includes, but is not limited to, incompleteness and/or incorrectness due to technological changes or any research conducted between the date of publication of this document and the date on which the product is acquired. Bostik reserves the right to amend the wording of this document. Bostik cannot be held liable for any damage, either directly or indirectly, due to the use of the product(s) depicted in this document. The user must read and understand the information in this document and other documents relating to the products prior to the use of the product. The user is responsible for performing all the requisite tests to make sure that the product is suitable for its intended use. We have no influence in what way the product is applied and/or any circumstances relating to events occurring during storage or transport and therefore we do not accept any liability for damage whatsoever. All deliveries are made exclusively in accordance with our general terms of conditions which have been filed at the Dutch Chamber of Commerce.



Den Braven

Bostik Singapore
1 Science Park Road, #04-01/5 The Capricorn, 117528 Singapore
T +65 6419 9161 | E

28-04-2024
16:00:54
MDT