



Tectane Spray Adhesive  
Multi-purpose adhesive for porous and non-porous substrates



Product Description

Spray Adhesive can be used for all minor adhesive problems in motor vehicle technology, trade, modeling, DIY, hobby and household.

Benefits

- Instant adhesive strength
- Adjustable nozzle

Applications

Spray Adhesive is suitable for paper, cardboard, wood, thin veneer, cork, leather, textiles, polystyrene foam, rubber, plastic foil (except PVC/PE).

Directions Of Use

Shake can well. Surfaces must be clean, dry, free of grease and residues. Non-porous materials: Apply on both surfaces, allow to dry for 15 minutes (+20°C), then assemble parts with high pressure. Porous materials: Apply on one surface and assemble with pressure immediately. Apply from a distance of approx. 20-25 cm. After use, turn can upside down and spray to clear valve.

Additional information

Application temperature		+5°C to +35°C
Base		Adhesive solution based on synthetic rubber and resin in a hydrocarbon/ ketone solvent blend
Curing time		Adhesive becomes tacky in 1 to 3 minutes and should be bonded within 10 to 20 minutes. Adhesive remains 'wet' for 15 to 25 minutes.
Temperature range_c		-25°C to +45°C

These are typical values

Limitations

Surface Preparations and Finishing

Cleaning

Colour(s)

- Colourless

Packaging

- Aerosol

For product specifications, please refer to the Product Detail Page

Shelf Life

Store between +5°C and +25°C in shaded conditions. Shelf life is 12 months when stored as recommended in original unopened packaging.





# Den Braven

## Technical Data Sheet

### Tectane Spray Adhesive

Multi-purpose adhesive for porous and non-porous substrates

#### Health & Safety

Product Safety Data Sheet must be read and understood before use.

These are available on request and via our websites

#### Warranty & Guarantee

Bostik warrants that its product complies, within its shelf life, to its specification.

#### Disclaimer

All information in this document and in all our other publications (including electronic ones) is based on our current knowledge and experience and is the exclusive (intellectual) property of Bostik. No part of this document may be copied, shown to third parties, reproduced, communicated to the public or used in any other way without Bostik written consent. The technical information in this document serves as an indication and is non-exhaustive. Bostik is not liable for any damage, either directly or indirectly, due to (editorial) errors, incompleteness and/or incorrectness of this document. This includes, but is not limited to, incompleteness and/or incorrectness due to technological changes or any research conducted between the date of publication of this document and the date on which the product is acquired. Bostik reserves the right to amend the wording of this document. Bostik cannot be held liable for any damage, either directly or indirectly, due to the use of the product(s) depicted in this document. The user must read and understand the information in this document and other documents relating to the products prior to the use of the product. The user is responsible for performing all the requisite tests to make sure that the product is suitable for its intended use. We have no influence in what way the product is applied and/or any circumstances relating to events occurring during storage or transport and therefore we do not accept any liability for damage whatsoever. All deliveries are made exclusively in accordance with our general terms of conditions which have been filed at the Dutch Chamber of Commerce.



Den Braven

Bostik Singapore  
1 Science Park Road, #04-01/5 The Capricorn, 117528 Singapore  
T +65 6419 9161 | E

27-04-2024  
20:39:36  
CEST