



Den Braven

Technical Data Sheet

Tectane Zinc Spray Matt

Corrosion protection



Product Description

Zinc Spray Matt is a cold galvanizing spray with high zinc content that protects steel and ferrous metals exposed to severe corrosive environments.

Benefits

- High resistance to weather effects, salt corrosion and chemicals
- High Purity Zinc (98%)
- Fast Drying
- Resistant to temperatures up to +50°C.
- Paintable

Applications

Can be used as a primer or to repair damaged zinc layers and in coating drilling, cutting and welding points.

Directions Of Use

Ideal application temperature +16°C to +25°C. Clean the entire surface to be treated carefully. Shake the can vigorously at least 30 seconds before use, then apply crosswise from a distance of 25-30 cm. After use the can should be inverted and the spray activated until the jet is cleared and only propellant is emitted.

Additional information

Application temperature	+16°C to +25°C
Base	Epoxy ester
Curing time	24 hours
Density	0.927
Extrusion rate gs	3.4
Film thickness coverage_m	50-80
Frost resistance during transportation	Up to -15°C
Pressure at 20c bar	4.0
Pressure at 50c bar	7.7
Re-coatable after hrs	24 hours
Salt spray test hrs	500 hours
Solid contents	33.5
Tack free time	60 minutes
Temperature range_c	-50°C to +500°C

These are typical values

Limitations

Surface Preparations and Finishing

Paintability

Zinc Spray Matt can be painted.

Cleaning

Colour(s)

- Zinc

Packaging

- Aerosol

For product specifications, please refer to the Product Detail Page



Den Braven

Better
results
through
knowledge

Technical Data Sheet

Tectane Zinc Spray Matt

Corrosion protection

Shelf Life

Storage between +5°C and +25°C and in shaded conditions. Shelf life is 24 months when stored as recommended in original unopened packaging.

Health & Safety

Product Safety Data Sheet must be read and understood before use. These are available on request and via our websites

Warranty & Guarantee

Bostik warrants that its product complies, within its shelf life, to its specification.

Disclaimer

All information in this document and in all our other publications (including electronic ones) is based on our current knowledge and experience and is the exclusive (intellectual) property of Bostik. No part of this document may be copied, shown to third parties, reproduced, communicated to the public or used in any other way without Bostik written consent. The technical information in this document serves as an indication and is non-exhaustive. Bostik is not liable for any damage, either directly or indirectly, due to (editorial) errors, incompleteness and/or incorrectness of this document. This includes, but is not limited to, incompleteness and/or incorrectness due to technological changes or any research conducted between the date of publication of this document and the date on which the product is acquired. Bostik reserves the right to amend the wording of this document. Bostik cannot be held liable for any damage, either directly or indirectly, due to the use of the product(s) depicted in this document. The user must read and understand the information in this document and other documents relating to the products prior to the use of the product. The user is responsible for performing all the requisite tests to make sure that the product is suitable for its intended use. We have no influence in what way the product is applied and/or any circumstances relating to events occurring during storage or transport and therefore we do not accept any liability for damage whatsoever. All deliveries are made exclusively in accordance with our general terms of conditions which have been filed at the Dutch Chamber of Commerce.



Den Braven

Bostik Singapore
1 Science Park Road, #04-01/5 The Capricorn, 117528 Singapore
T +65 6419 9161 | E

02-05-2024
17:11:07
CEST