

## Technical Data Sheet

## Zwaluw Elast-O-Foam

Airtight, flexible high insulating polyurethane foam



## **Product Description**

Zwaluw Elast-O-Foam is a professional flexible 1-component gun foam based on polyurethane. The permanent flexibility creates a sustainable and highly insulating (airtight) seal. Zwaluw Elast-O-Foam is tested according to EN1026 for air loss at 1050Pa. Elast-O-Foam has excellent adhesion, durable sealing functions with high insulation values. Elast-O-Foam offers an A + label for VOC content.

#### **Benefits**

- Extreme low air loss, most air tight foam available on the market
- Flexible
- Tested to 1050 Pa
- · Provides best sound reduction
- High yield

### Applications

Zwaluw Elast-O-Foam is specifically developed for creating airtight and thermally insulated joints around window frames. Also suitable in construction, partition walls, ceiling and floor joints, surface penetration of pipes and tubes through walls and floors. Ideal for use in Passive Housing and energy neutral buildings.

### **Directions Of Use**

Canister temperature:  $+5^{\circ}$ C to  $+30^{\circ}$ C (recommended  $+15^{\circ}$ C to  $+25^{\circ}$ C) Application temperature (applies to environment and substrates):  $-5^{\circ}$ C to  $+35^{\circ}$ C (recommended  $+15^{\circ}$ C to  $+25^{\circ}$ C) Hold the

canister with the valve turned upwards and affix an applicator gun with NBS-thread to the canister. We recommend a NBS Gold (see instructions in the gun box). Shake the canister vigorously prior to use at least 20 times. Turn canister upside down and apply the foam. To regulate the flow of the foam, loosen the valve at the back of the handle. Fill the cavity for 70%, in case of low humidity, lightly spray the foam with water. The foam will expand to fill the rest. When fixing window frames, use spacers and wedges to hold the frame in place for approximately 24 hours until the foam is fully cured. Protect eyes, wear gloves and protective gear. Floor-covering and furniture to be covered with paper or plastic foil. Joints wider and deeper than 4 cm should be filled in multiple lavers. Wait 15-30 minutes between applications. Before each application lightly spray with water. Only use in well ventilated areas. Store canister upright between +5°C and +25°C. Pressurized container! Protect from sunlight and do not expose to temperatures exceeding + 50°C. Do not pierce or burn, even after use. Contains flammable propellants. Do not spray on a naked flame or any incandescent material. Keep away from sources of ignition. No smoking. For more information see Technical Bulletins in the Knowledge Base on our website www.denbraven.com.



05-05-2024 16:54:29 CEST



# **Technical Data Sheet**

## Zwaluw Elast-O-Foam

Airtight, flexible high insulating polyurethane foam

## Additional information

| Application temperature                  |            | -5°C to +35°C                       |
|--|------------|-------------------------------------|
| Base                                     |            | Polyurethane                        |
| Closed cells                             |            | ±70%                                |
| Curing time                              |            | 80-100 minutes                      |
| Cutting time                             | EN 17333-3 | 20-40 minutes                       |
| Density                                  |            | 20-25 kg/m3                         |
| Dimensional stability                    |            | -5% < DS < 0%                       |
| Fire behaviour                           |            | В3                                  |
| Joint sound insulation                   |            | 63 dB                               |
| Movement Capability                      |            | 25%                                 |
| Permeability                             | EN 1026    | a ≤ 0,001 dm3/<br>m.s. @ 1050<br>Pa |
| Permeability test                        |            | Up to 1050 Pa                       |
| Tack free time                           | EN 17333-3 | 6-10 minutes                        |
| Temperature resistance                   |            | -40°C to +90°C                      |
| Thermal conductivity                     |            | 30-35 mW/m.K                        |
| Total foam yield                         | EN 17333-1 | 750 ml = 30-35<br>liter             |
| Water absorption wp                      |            | 0,15kg/m²                           |
| Water vapour diffusion resistance factor |            | 36µ                                 |
| Water vapour diffusion sd                |            | 1,3m                                |

These are typical values

### Limitations

- Not suitable for PE, PP, PC, PMMA, PTFE, soft plastics, neoprene and bituminous substrates
- Not suitable for permanent water load. Not suitable for use (eg filling) in cavities with insufficient moisture

## Surface Preparations and Finishing

Substrates must be clean and free of dust, oil and grease. It is important to moisten substrates slightly before use as this improves adhesion and finished cell structure of the foam.

### Paintability

Can be painted or covered with sealant/plaster when fully cured.

#### Cleaning

Fresh foam can be removed immediately with Zwaluw Universal PU-Cleaner. After curing surplus foam can be removed with a knife or spatula and the foam surface can be finished.

## Colour(s)

White

## Packaging

- Can
- Recypur

For product specifications, please refer to the Product Detail Page

### Shelf Life

If kept stored in a cool, dry place, in unopened original packaging, between +5°C and +25°C, shelf life is up to 12 months from production date. Store the canisters in an upright position.

### Certifications

|                     | EN 12086 Water vapour transmission<br>EN 1609 Water vapour patial immersion<br>ISO 717-1 Joint Sound Insulation |
|---------------------|---|
| ECT - CO<br>Werning | EMICODE EC1 Plus – very low emission  |

## Health & Safety

Product Safety Data Sheet must be read and understood before use. These are available on request and via our websites





# **Technical Data Sheet**

## Zwaluw Elast-O-Foam

Airtight, flexible high insulating polyurethane foam

#### Warranty & Guarantee

Bostik warrants that its product complies, within its shelf life, to its specification.

#### Disclaimer

All information in this document and in all our other publications (including electronic ones) is based on our current knowledge and experience and is the exclusive (intellectual) property of Bostik. No part of this document may be copied, shown to third parties, reproduced, communicated to the public or used in any other way without Bostik written consent. The technical information in this document serves as an indication and is non-exhaustive. Bostik is not liable for any damage, either directly or indirectly, due to (editorial) errors, incompleteness and/or incorrectness of this document. This includes, but is not limited to, incompleteness and/or incorrectness due to technological changes or any research conducted between the date of publication of this document. Bostik cannot be held liable for any damage, either directly or indirectly, due to the use of the product is acquired. Bostik reserves the right to amend the wording of this document. Bostik cannot be held liable for any damage, either directly or indirectly, due to the use of the product is less the right to ament the wording of this document. Bostik cannot be held liable for any damage, either directly or indirectly, due to the use of the product is less to make sure that the product is suitable for its intended use. We have no influence in what way the product is applied and/or any circumstances relating to events occurring during storage or transport and therefore we do not accept any liability for damage whatsoever. All deliveries are made exclusively in accordance with our general terms of conditions which have been filed at the Dutch Chamber of Commerce.

