

Bostik Bostik FP402 Fireseal Silicone

High quality fire resistants silicone sealant



Product Description

Bostik FP402 FIRESEAL SILICONE is a fire retardant, elastic, neutrally curing silicone sealant. Bostik FP402 FIRESEAL SILICONE is fire resistant for up to 4 hours in linear (movement) joints. Absorbs up to 25% of movement.

Benefits

- Tested according to EN 1366-4
- Up to 4 hours of fire resistance
- · Can be applied in joints up to 30 mm wide
- In combination with FP404 PU GUN FOAM in joints up to 40 mm wide
- Excellent processing, does not slump
- Joint movement up to 25%
- UV, water and weather resistant
- · Airtight sealing
- · For internal and external use
- B1 fire behaviour

Applications

Bostik FP402 FIRESEAL SILICONE was specifically developed for fire resistant sealing of connection and expansion joints in construction and is fire resistant in case of fire. Prevents the expansion of fire, smoke or toxic gases. Fire resistance tested according to EN 1366-4 up to 180 minutes in a gap of 30 mm wide.

Bostik Benelux B.V

Denariusstraat 11, 4903 RC Oosterhout, The Netherlands Phone: +31 (0)162491000, E-mail: info@bostik.com www.bostik.com | www.denbraven.com

Combined with Bostik FP404 FIRE RETARDENT PU GUN FOAM up to 180 minutes in a gap of 40 mm wide. Ensure that you choose the correct fire resistance for your application by consulting the classification and test reports.

Directions Of Use

A joint with the correct dimensions is able to absorb movements between building materials. The joint depth should always be in the correct relationship of the joint width. A general rule is the ratio of joint depth to the width of the joint with a joint width up to 10 mm is 1:1, with a minimum of 5 mm in width and depth. For joints wider than 10 mm, the depth is the width divided by 3 plus 6 mm.

Additional information

100 % modulus	DIN 53504 S2	0,40 N/mm²
Application rate	@ Ø3 mm/6,3 bar	150 g/min
Application temperature		+5°C to +40°C
Base		Neutral oxime
Curing time	@ +23°C/50% RH	2 mm/24 hours
Density	ISO 1183-1	1,24 g/ml
Elongation at break	DIN 53504 S2	635%
Flow	ISO 7390	< 2 mm
Joint movement		25%
Shorea hardness	DIN 53505	20
Skin formation	DBTM 16	7-8 minutes @ +23°C/50% RH
Temperature resistance		-40°C to +120°C
Tensile strength	DIN 53504 S2	1,30 N/mm²

These are typical values

Limitations

 Not suitable for PE, PP, PC, PMMA, PTFE, soft plastics, neoprene and bituminous substrates

> 13-05-2024 17:56:41 CEST



Bostik Bostik FP402 Fireseal Silicone

High quality fire resistants silicone sealant

Surface Preparations and Finishing

Application temperature: +5°C to +40°C (applies to environment and substrates). All substrates must be solid, clean, dry, and free of grease and dust. Clean substrates with Bostik Cleaner. Bostik FP402 FIRESEAL SILICONE adheres perfectly without the use of primer to most non porous substrates. Porous substrates to be pre-treated with Primer. Always test adhesion prior to application. Use Bostik Finisher to smoothen the joint.

Paintability

Bostik FP402 FIRESEAL SILICONE is not paintable. We recommend covering the edges of the joint with masking tape to prevent surfaces that need to be painted from being contaminated by silicone.

Cleaning

Tools should be cleaned after use with water. Hands can be cleaned with Bostik Wipes and/or water and soap. Cured material can only be mechanically removed.

Colour(s)

- Black
- White
- Concrete Grey

Packaging

- Cartridge
- Sausage


For product specifications, please refer to the Product Detail Page

Shelf Life

In unopened original packaging between +5°C and +25°C, shelf life up to 12 months from production date, stored in a dry place.

Certifications

EN 1366-4:2006+A1:2010
DIN 4102-1 Reaction to fire



Health & Safety

Product Safety Data Sheet must be read and understood before use. These are available on request and via our websites

Warranty & Guarantee

Bostik warrants that its product complies, within its shelf life, to its specification.

Disclaimer

All information in this document and in all our other publications (including electronic ones) is based on our current knowledge and experience and is the exclusive (intellectual) property of Bostik. No part of this document may be copied, shown to third parties, reproduced, communicated to the public or used in any other way without Bostik written consent. The technical information in this document serves as an indication and is non-exhaustive. Bostik is not liable for any damage, either directly or indirectly, due to (editorial) errors, incompleteness and/or incorrectness of this document. This includes, but is not limited to, incompleteness and/or incorrectness due to technological changes or any research conducted between the date of publication of this document and the date on which the product is acquired. Bostik reserves the right to amend the wording of this document. Bostik cannot be held liable for any damage, either directly or indirectly, due to the use of the product(s) depicted in this document. The user must read and understand the information in this document and other documents relating to the products prior to the use of the product. The user is responsible for performing all the requisite tests to make sure that the product is suitable for its intended use. We have no influence in what way the product is applied and/or any circumstances relating to events occurring during storage or transport and therefore we do not accept any liability for damage whatsoever. All deliveries are made exclusively in accordance with our general terms of conditions which have been filed at the Dutch Chamber of Commerce.

Denariusstraat 11, 4903 RC Oosterhout, The Netherlands Phone: +31 (0)162491000, E-mail: info@bostik.com www.bostik.com | www.denbraven.com