

## Bostik S520 SILICONE BATH & KITCHEN A

Low modulus acetoxysilicone for sanitary and kitchen applications



### Product Description

BOSTIK S520 SILICONE BATH & KITCHEN A is a versatile acetoxysilicone sealant for sanitary joints, which cures under influence of humidity to form a durable elastic rubber.

### Benefits

- Excellent resistance to water
- Mould resistant
- Colourfast
- Excellent adhesion to glass, painted wood, ceramic, enameled substrates
- For interior and exterior use

### Applications

BOSTIK S520 SILICONE BATH & KITCHEN A is specially developed for durable elastic sealing of expansion joints in sanitary applications such as kitchens, bathrooms, showers and industrial applications.

### Directions Of Use

A joint with the correct dimensions is able to absorb movements between building materials. The joint depth should always be in the correct relationship of the joint width. A general rule is the ratio of joint depth to the width of the joint with a joint width up to 10mm is 1:1, with a minimum of 5mm in width and depth. For joints wider than 10mm, the depth is the width divided by 3 plus 6mm.

### Bostik Benelux B.V

Denariusstraat 11, 4903 RC Oosterhout, The Netherlands  
Phone: +31 (0)162491000, E-mail: [info@bostik.com](mailto:info@bostik.com)  
[www.bostik.com](http://www.bostik.com) | [www.denbraven.com](http://www.denbraven.com)

### Additional information

100 % modulus		0,29 N/mm <sup>2</sup>
Application rate	6.3 bar/3mm	465 g/min
Application temperature		+5°C till +40°C
Base		Silicone
Density		0,97 g/ml
Elongation at break		465%
Frost resistance during transportation		till -15°C
Shorea hardness	DIN 53505	14
Skin formation	@23°C/55% RH	5-6 min
Temperature resistance		-40°C till +120°C
Tensile strength		0,95 N/mm <sup>2</sup>
Viscosity		75

*These are typical values*

### Limitations

- Not suitable for applications on concrete, marble, lead, copper and galvanized steel
- Not suitable for PE, PP, PC, PMMA, PTFE, neoprene and bituminous substrates

### Surface Preparations and Finishing

Application temperature + 5°C to + 40°C (applies to environment and substrates). All substrates must be solid, clean and free of grease and dust. Clean substrates with Cleaner. BOSTIK S520 SILICONE BATH & KITCHEN A adheres perfectly without the use of primer to most non porous substrates. Porous substrates to be pre-treated with BOSTIK Primer. Always test adhesion prior to application. Use BOSTIK Finisher to smooth the joint.

### Paintability

BOSTIK S520 SILICONE BATH & KITCHEN A is not paintable. We recommend covering the edges of the joint with masking tape to

## Bostik S520 SILICONE BATH & KITCHEN A

Low modulus acetoxysilicone for sanitary and kitchen applications

prevent surfaces that need to be painted from being contaminated by silicone.

### Cleaning

Tools should be cleaned after use with water. Hands can be cleaned with BOSTIK Wipes and/or water and soap. Cured material can only be mechanically removed.

### Colour(s)

- Transparent
- White
- Brown
- Concrete Grey
- Black

### Packaging



- Cartridge

*For product specifications, please refer to the Product Detail Page*

### Shelf Life

In unopened original packaging between +5°C and +25°C, shelf life till 18 months after production date, stored in a dry place.

### Certifications

	EN 15651-1: F-EXT-INT-CC 12.5E
	EN 15651-2: G-CC EN 15651-3: S XS1
	A+ French VOC Regulation

### Health & Safety

Product Safety Data Sheet must be read and understood before use. These are available on request and via our websites

### Warranty & Guarantee

Bostik warrants that its product complies, within its shelf life, to its specification.

### Disclaimer

All information in this document and in all our other publications (including electronic ones) is based on our current knowledge and experience and is the exclusive (intellectual) property of Bostik. No part of this document may be copied, shown to third parties, reproduced, communicated to the public or used in any other way without Bostik written consent. The technical information in this document serves as an indication and is non-exhaustive. Bostik is not liable for any damage, either directly or indirectly, due to (editorial) errors, incompleteness and/or incorrectness of this document. This includes, but is not limited to, incompleteness and/or incorrectness due to technological changes or any research conducted between the date of publication of this document and the date on which the product is acquired. Bostik reserves the right to amend the wording of this document. Bostik cannot be held liable for any damage, either directly or indirectly, due to the use of the product(s) depicted in this document. The user must read and understand the information in this document and other documents relating to the products prior to the use of the product. The user is responsible for performing all the requisite tests to make sure that the product is suitable for its intended use. We have no influence in what way the product is applied and/or any circumstances relating to events occurring during storage or transport and therefore we do not accept any liability for damage whatsoever. All deliveries are made exclusively in accordance with our general terms of conditions which have been filed at the Dutch Chamber of Commerce.

### Bostik Benelux B.V

Denariusstraat 11, 4903 RC Oosterhout, The Netherlands  
Phone: +31 (0)162491000, E-mail: [info@bostik.com](mailto:info@bostik.com)  
[www.bostik.com](http://www.bostik.com) | [www.denbraven.com](http://www.denbraven.com)

19-05-2024  
13:39:45  
CEST