

Bostik FP404 Fire Retardent PU Gun Foam FIRE RETARDENT POLYURETHAN GUN FOAM



Product Description

Bostik FP404 FIRE RETARDENT PU GUN FOAM is a 1-component fire resistant polyurethane foam which offers a fire resistance of up to 120 minutes. In combination with other Bostik FireProtect® products Bostik FP404 FIRE RETARDENT PU GUN FOAM reaches up to 240 minutes of fire resistance! Professional polyurethane fills and fixes foam with a structure of fine cells. High thermal and acoustic insulation.

Benefits

- Tested according to EN 1366-4
- For use in joints from 5 mm to 30 mm wide
- Combined with Bostik FP402 FIRESEAL SILICONE in joints from 5 mm to 40 mm wide
- Separately applied, fire resistant up to 2 hours, combined with other Bostik FireProtect® products up to 4 hours
- Fire behaviour B1
- Fast processing
- Tack free after 8 to 12 minutes

Applications

Bostik FP404 FIRE RETARDENT PU GUN FOAM was specifically developed for fire resistant sealing and filling of joints and seams in certain areas where fire resistance is required. Fire resistance tested according to EN 1366-4 up to 60 minutes in a 20 mm wide gap. In combination with Bostik FP402 FIRESEAL SILICONE, Bostik FP404

FIRE RETARDENT PU GUN FOAM will provide up to 180 minutes fire resistance in a 40 mm wide gap. In combination with Bostik FP403 FIRESEAL HYBRID, Bostik FP404 FIRE RETARDENT PU GUN FOAM will provide up to 240 minutes fire resistance in a 40 mm wide gap. Ensure that you choose the correct fire resistance for your application by consulting the classification and test reports.

Directions Of Use

Canister temperature: + 5°C to + 30°C (although +15°C to + 25°C is recommended) Application temperature (applies to environment and substrates): + 5°C to + 35°C (recommended + 15°C to + 25°C). Hold the canister with the valve turned upwards and affix an applicator gun with NBS thread to the canister. We recommend a NBS Gold (see instructions in the gun box). Shake the canister vigorously prior to use at least 30 times. Turn canister upside down and apply the foam. To regulate the flow of the foam, loosen the valve at the back of the handle. Half fill the cavity and, in case of low humidity, lightly spray the foam with water. The foam will expand to fill the rest. Protect eyes, wear gloves and protective gear. Floorcovering and furniture to be covered with paper or plastic foil. Joints wider and deeper than 4cm should be filled in multiple layers. Wait 15-30 minutes between applications. Before each application lightly spray with water. Only use in well ventilated areas. Store canister upright between + 5°C and + 25°C. Pressurized container! Protect from sunlight and do not expose to temperatures exceeding + 50°C. Do not pierce or burn, even after use. Contains flammable propellants. Do not spray on a naked flame or any incandescent material. Keep away from sources of ignition. No smoking.

Bostik Benelux B.V

Denariusstraat 11, 4903 RC Oosterhout, The Netherlands
Phone: +31 (0)162491000, E-mail: info@bostik.com
www.bostik.com | www.denbraven.com

13-05-2024
21:26:51
CEST

Bostik FP404 Fire Retardent PU Gun Foam

FIRE RETARDENT POLYURETHAN GUN FOAM

Additional information

| | | |
|-------------------------|------------|-------------------------|
| Application temperature | | +5°C to +35°C |
| Base | | Polyurethane |
| Closed cells | | ± 70% |
| Curing time | | 80-100 minutes |
| Cutting time | EN 17333-3 | 20-40 minutes |
| Density | | 15-20 kg/m ³ |
| Fire behaviour | DIN 4102-1 | B1 |
| Joint sound insulation | | 61db |
| Tack free time | EN 17333-3 | 8-12 minutes |
| Temperature resistance | | -40°C to +90°C |
| Thermal conductivity | | 30-35 mW/m.K |
| Total foam yield | EN 17333-1 | 750 ml = 40-45 liter |

These are typical values

Limitations

- Not suitable for PE, PP, PC, PMMA, PTFE, soft plastics, neoprene and bituminous substrates
- Not suitable for permanent water load. Not suitable for use (eg filling) in cavities with insufficient moisture

Surface Preparations and Finishing

Substrates must be clean and free of dust, oil and grease. It is important to moisten substrates slightly before use as this improves adhesion and finished cell structure of the foam.

Paintability

Bostik FP404 FIRE RETARDENT PU GUN FOAM is paintable with water based and synthetic paints. We recommend testing compatibility with paint prior to application.

Cleaning

Fresh foam can be removed immediately with Bostik P100 FOAM'N'CLEAN POWER. After curing surplus foam can be removed with a knife or spatula and the foam surface can be finished.

Colour(s)

- Red

Packaging


- Can

For product specifications, please refer to the Product Detail Page

Shelf Life

If kept in unopened original packaging between +5°C and +25°C and stored in a dry place, the shelf life is up to 18 months from production date. Store the canisters in an upright position.

Certifications

| | |
|---|--|
| | EN 1366-4:2006+A1:2010 EN 13501-2 Classification of fire resistance DIN 4102-1 Reaction to fire VOC emissions ISO 16000 |
|  | EMICODE EC1 Plus – very low emission |

Health & Safety

Product Safety Data Sheet must be read and understood before use. These are available on request and via our websites

Warranty & Guarantee

Bostik warrants that its product complies, within its shelf life, to its specification.

Disclaimer

All information in this document and in all our other publications (including electronic ones) is based on our current knowledge and experience and is the exclusive (intellectual) property of Bostik. No part of this document may be copied, shown to third parties, reproduced, communicated to the public or used in any other way without Bostik written consent. The technical information in this document serves as an indication and is non-exhaustive. Bostik is not liable for any damage, either directly or indirectly, due to (editorial) errors, incompleteness and/or incorrectness of this document. This includes, but is not limited to, incompleteness and/or incorrectness due to technological changes or any research conducted between the date of publication of this document and the date on which the product is acquired. Bostik reserves the right to amend the wording of this document. Bostik cannot be held liable for any damage, either directly or indirectly, due to the use of the product(s) depicted in this document. The user must read and understand the information in this document and other documents relating to the products prior to the use of the product. The user is responsible for performing all the requisite tests to make sure that the product is suitable for its intended use. We have no influence in what way the product is applied and/or any circumstances relating to events occurring during storage or transport and therefore we do not accept any liability for damage whatsoever. All deliveries are made exclusively in accordance with our general terms of conditions which have been filed at the Dutch Chamber of Commerce.

Bostik Benelux B.V

Denariusstraat 11, 4903 RC Oosterhout, The Netherlands
Phone: +31 (0)162491000, E-mail: info@bostik.com
www.bostik.com | www.denbraven.com

13-05-2024
21:26:51
CEST