



Den Braven

Technical Data Sheet

Zwaluw Purfoam-2C Sprint B2

Fast 2-component mounting and insulation foam



Product Description

Zwaluw Purfoam-2C Sprint B2 is a fast curing 2-component mounting and insulating polyurethane foam with high dimensional stability, which cures regardless of moisture and joint measurement.

Benefits

- Excellent adhesion to concrete, masonry, wood and many plastics
- Excellent properties for heat resistance and noise reduction
- For filling cavities with insufficient access to moisture

Applications

Zwaluw Purfoam-2C Sprint B2 was developed to fill joints between windows and door frames. Due to its thermal properties and the 2-component system Zwaluw Purfoam-2C Sprint B2 can also be used for joints with insufficient moisture access. Zwaluw Purfoam-2C Sprint B2 has excellent adhesion to concrete, brick, stone, plaster, wood, metal and many plastics like EPS and XPS, rigid PU foam and uPVC.

Directions Of Use

Canister temperature: +15°C to +25°C Application temperature (applies to environment and substrates): +10°C to +35°C At lower temperatures or wider joints, let the foam sit for 1 to 2 minutes after activation, before application. Rotate the disk at the bottom of the canister 6 times and shake the canister vigorously at least 20x. Canister must be used immediately after activation within the indicated time. The Purfoam-2C Fast heats after activation (risk of

bursting!). Remove the cap and screw the straw onto the canister and shake vigorously. Turn canister upside down and apply the foam by using the handle. The foam should be evenly coloured. In case of colour differences, shake canister again. Support doors and window frames for at least 3 hours after application so the Purfoam-2C Fast can cure. Floor-covering and furniture to be covered with paper or plastic foil. Only use in well ventilated areas. Store canister upright between +5°C and +25°C. Pressurized container! Protect from sunlight and do not expose to temperatures exceeding + 50°C. Do not pierce or burn, even after use. Contains flammable propellants. Do not spray on a naked flame or any incandescent material. Keep away from sources of ignition. No smoking. For more information see Technical Bulletins in the Knowledge Base on our website www.denbraven.com.

Additional information

Application temperature		+10°C to +35°C
Base		Polyurethane
Closed cells		± 70%
Curing time		10-20 minutes
Cutting time	EN 17333-3	10 minutes
Density		40 kg/m ³
Fire behaviour		B2
Tack free time	EN 17333-3	6 minutes
Temperature resistance		-40°C to +90°C
Thermal conductivity		30-35 mW/m.K
Total foam yield	EN 17333-1	240 ml = 6 liter

These are typical values

Limitations

- Not suitable for PE, PP, PC, PMMA, PTFE, soft plastics, neoprene and bituminous substrates
- Not suitable for permanent water load. Not suitable for use (eg filling) in cavities with insufficient moisture

Surface Preparations and Finishing

Substrates must be clean and free of dust, oil and grease. Dry the substrates before use. Porous building materials like concrete and gypsum should be pre-treated with PU Primer.



Den Braven

Technical Data Sheet

Zwaluw Purfoam-2C Sprint B2
Fast 2-component mounting and insulation foam

Paintability

Can be painted or coated with plaster or acrylic sealant.

Cleaning

Fresh foam can be removed immediately with Zwaluw Universal PU-Cleaner. After curing surplus foam can be removed with a knife or spatula and the foam surface can be finished.

Colour(s)

- Purple

Packaging



- Aerosol

For product specifications, please refer to the Product Detail Page

Shelf Life

If kept stored in a cool, dry place, in unopened original packaging, between +5°C and +25°C, shelf life is up to 18 months from production date. Store the canisters in an upright position.

Certifications

	DIN 4102-1 Reaction to fire
	A+ French VOC Regulation
	Emicode EC1 Plus

Health & Safety

Product Safety Data Sheet must be read and understood before use. These are available on request and via our websites

Warranty & Guarantee

Bostik warrants that its product complies, within its shelf life, to its specification.

Disclaimer

All information in this document and in all our other publications (including electronic ones) is based on our current knowledge and experience and is the exclusive (intellectual) property of Bostik. No part of this document may be copied, shown to third parties, reproduced, communicated to the public or used in any other way without Bostik written consent. The technical information in this document serves as an indication and is non-exhaustive. Bostik is not liable for any damage, either directly or indirectly, due to (editorial) errors, incompleteness and/or incorrectness of this document. This includes, but is not limited to, incompleteness and/or incorrectness due to technological changes or any research conducted between the date of publication of this document and the date on which the product is acquired. Bostik reserves the right to amend the wording of this document. Bostik cannot be held liable for any damage, either directly or indirectly, due to the use of the product(s) depicted in this document. The user must read and understand the information in this document and other documents relating to the products prior to the use of the product. The user is responsible for performing all the requisite tests to make sure that the product is suitable for its intended use. We have no influence in what way the product is applied and/or any circumstances relating to events occurring during storage or transport and therefore we do not accept any liability for damage whatsoever. All deliveries are made exclusively in accordance with our general terms of conditions which have been filed at the Dutch Chamber of Commerce.

Better results through knowledge



Den Braven

Bostik Benelux B.V
Denariusstraat 11, 4903 RC Oosterhout
T +31 (0)162491000 | E info@bostik.com

05-05-2024
01:25:36
CEST