



# Den Braven

## Technical Data Sheet

### Zwaluw Compress Band BG1

Impregnated polyurethane foam joint sealing tape



#### Product Description

Zwaluw Compress Band BG1 is an impregnated pre-compressed polyurethane foam joint sealing tape with soft foam with acrylate dispersion impregnation, accessory agents and filling agents. Zwaluw Compress Band BG1 is a one sided adhesive. After application the pre-compressed tape will expand slowly to fill the joint. At a compression of at least 30% of the maximum width the impregnated foam is watertight against driving rain up to 600 Pa.

#### Benefits

- Resistant to driving rain > 600 Pa
- Joint sound insulation RST, W max. 59 dB
- For heavy-duty primary and cross joints
- Thermal conductivity  $\lambda=0.0429$  W/mK
- Building materials class B1
- Weather resistant in the long term

#### Applications

Zwaluw Compress Band BG1 can be put to universal use for the sealing of joints in structural engineering. The preferred areas of use are window construction, wood construction, prefabricated construction and masonry, framework construction and concrete construction. Zwaluw Compress Band BG1 provides advantages when it comes to sealing connection joints and expansion joints between various building components, and when sealing foils in roof extensions, so they are windproof. Zwaluw Compress Band BG1 is specifically used in interior work for sealing connection joints due to its good sound insulation values. Zwaluw Compress Band BG1 on the roll can be universally used, and also be inserted in existing joints due to the pre-compression. Zwaluw Compress Band BG1 can be used in airtight or passive house details in combination with Zwaluw Compress Band 2D or Zwaluw Window Foil Interior.

#### Directions Of Use

For a complete overview see our website or contact Den Braven.

#### Additional information

Application temperature		+5°C to +30°C
Compression factor		minimal 20
Density		120-150 kg/m <sup>3</sup>
Elongation at break		> 200%
Fire behaviour		B1
Frost resistance during transportation		Up to -15°C
Joint permeability	EN 1027	≤ 900 Pa
Joint sound insulation		59 dB; RST,W
Permeability	EN 1026	a = 0,2900 m <sup>3</sup> /h.m
SD Value		< 0,5 m
Temperature resistance		- 0°C to +100°C, max. +130°C briefly

*These are typical values*

#### Limitations

#### Surface Preparations and Finishing

All surfaces must be clean, dry and free of dust, grease and other loose material. Adhesion tests prior to application are recommended. Clean the surfaces thoroughly by using Zwaluw Cleaner.

#### Paintability

Zwaluw Compress Band BG1 is paintable with water based and most 2 component paints. Synthetic paints can dry slower. We recommend testing compatibility with paint prior to application.

#### Cleaning

Surfaces can be cleaned by using Zwaluw Cleaner.

#### Colour(s)

- Anthracite



Den Braven

Bostik Benelux B.V  
Denariusstraat 11, 4903 RC Oosterhout  
T +31 (0)162491000 | E info@bostik.com

02-05-2024  
00:05:13  
MDT



Den Braven



Technical Data Sheet

Zwaluw Compress Band BG1  
Impregnated polyurethane foam joint sealing tape

Packaging


- Roll

For product specifications, please refer to the Product Detail Page

Shelf Life

In unopened original packaging between +5°C and +25°C, shelflife up to 18 months from date of production, stored in a dry place.

Certifications

	Emicode EC1 Plus
	BRL 2802 KOMO SKH A+ (Eurofins ISO 16000)

Health & Safety

Product Safety Data Sheet must be read and understood before use.  
These are available on request and via our websites

Warranty & Guarantee

Bostik warrants that its product complies, within its shelf life, to its specification.

Disclaimer

All information in this document and in all our other publications (including electronic ones) is based on our current knowledge and experience and is the exclusive (intellectual) property of Bostik. No part of this document may be copied, shown to third parties, reproduced, communicated to the public or used in any other way without Bostik written consent. The technical information in this document serves as an indication and is non-exhaustive. Bostik is not liable for any damage, either directly or indirectly, due to (editorial) errors, incompleteness and/or incorrectness of this document. This includes, but is not limited to, incompleteness and/or incorrectness due to technological changes or any research conducted between the date of publication of this document and the date on which the product is acquired. Bostik reserves the right to amend the wording of this document. Bostik cannot be held liable for any damage, either directly or indirectly, due to the use of the product(s) depicted in this document. The user must read and understand the information in this document and other documents relating to the products prior to the use of the product. The user is responsible for performing all the requisite tests to make sure that the product is suitable for its intended use. We have no influence in what way the product is applied and/or any circumstances relating to events occurring during storage or transport and therefore we do not accept any liability for damage whatsoever. All deliveries are made exclusively in accordance with our general terms of conditions which have been filed at the Dutch Chamber of Commerce.



Den Braven

Bostik Benelux B.V  
Denariusstraat 11, 4903 RC Oosterhout  
T +31 (0)162491000 | E info@bostik.com

02-05-2024  
00:05:13  
MDT